



Standard Test Method for Lithium and Sodium in Lubricating Greases by Flame Photometer¹

This standard is issued under the fixed designation D 3340; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers determination of the lithium and sodium content of lubricating greases by means of a flame photometer.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.3 The preferred units are mass % and accepted SI units. The values given in parentheses are for information only.

2. Referenced Documents

2.1 *ASTM Standards:*

D 1193 Specification for Reagent Water²

3. Summary of Test Method

3.1 The sulfated ash of the grease is extracted with water and the lithium and sodium content of the resulting solution is determined by means of a suitable flame photometer.

4. Significance and Use

4.1 Lubricating greases can contain the lithium soap of hydroxy stearic acid or the sodium soap of various fatty acids as thickeners. The determination of total lithium or total sodium is a measure of the amount of thickener in the grease.

5. Apparatus

5.1 *Flame Photometer*, suitably equipped to determine lithium and sodium over a range from 0 to 15 mg/L lithium and from 0 to 5 mg/L sodium.

6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that

all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.³ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Type II of Specification D 1193.

6.3 *Lithium Sulfate, Stock Solution*—1.188 g of lithium sulfate dried to constant weight at 180°C (356°F), is dissolved in water and made up to 1 L. This will contain 150 mg/L lithium.

6.4 *Sodium Sulfate, Stock Solution*—0.1544 g of sodium sulfate, dried to constant weight at 105°C (221°F), is dissolved in water and made up to 1 L. This will contain 50 mg/L sodium.

6.5 *Sulfuric Acid* (rel. den. 1.84)—Concentrated sulfuric acid (H₂SO₄).

7. Sampling

7.1 A homogeneous sample shall be obtained to ensure quantitative analytical results.

8. Procedure

8.1 Weigh to the nearest 1 mg approximately 1 g of the grease into a platinum dish or crucible. Heat the dish until the sample can be ignited with a flame. Maintain at such a temperature that the sample burns at a uniform and moderate rate, leaving only ash and carbon when the burning ceases.

8.2 Cool the dish and completely moisten the residue by the dropwise addition of concentrated sulfuric acid. Heat the dish at a low temperature, taking care to avoid spattering of the contents, and continue heating until fumes are no longer evolved. Place the dish in a furnace at 550 ± 25°C (1022 ± 45°F) and continue heating until the oxidation of the carbon is practically complete.

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.03 on Elemental Analysis.

Current edition approved May 10, 2003. Published July 2003. Originally approved in 1974. Last previous edition approved in 1998 as D 3340-98.

² *Annual Book of ASTM Standards*, Vol 11.01.

³ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

TABLE 1 Precision Values for Lithium and Sodium (Mass %)

Lithium, <i>x</i>	Repeatability $0.014(x)^{2/5}$	Reproducibility $0.075(x)^{2/5}$
0.01	0.002	0.011
0.05	0.004	0.022
0.1	0.005	0.029
0.2	0.007	0.039
0.3	0.008	0.046
0.4	0.009	0.052
Sodium, <i>x</i>	Repeatability $0.029(x)^{2/5}$	Reproducibility $0.166(x)^{2/5}$
0.01	0.004	0.026
0.05	0.008	0.050
0.1	0.011	0.066
0.2	0.015	0.087
0.3	0.017	0.102
0.4	0.020	0.115
0.5	0.022	0.125
0.6	0.023	0.135
0.7	0.025	0.143
0.8	0.026	0.151

8.3 Cool and repeat 8.2 to complete the sulfation.

8.4 Extract the sulfated ash with hot distilled water and transfer the aqueous extract, filtering if necessary, to a 100-mL volumetric flask. Allow to cool and make up to the mark with distilled water.

8.5 Prepare the following fresh calibration standards by appropriate dilution of the stock solutions:

8.5.1 *Lithium Sulfate*—Solutions containing 0, 3, 6, 9, 12 and 15 mg/L lithium.

8.5.2 *Sodium Sulfate*—Solutions containing 0, 1, 2, 3, 4, and 5 mg/L sodium.

8.6 Obtain the flame photometer readings for each calibration standard and prepare curves relating concentration to photometer reading.

8.7 Obtain readings for the extract derived from 8.4 and determine the lithium and sodium contents from the calibration curves.

NOTE 1—Further dilution may be necessary.

9. Calculation and Report

9.1 Calculate the lithium content of the grease as follows:

$$\text{Lithium, mass \%} = X/100 W \quad (1)$$

where:

X = lithium content of the water extract, mg/L lithium (see 8.7), and

W = mass of the grease taken, g.

Modify the formula if further dilution of the water extract was necessary, for example, if further dilution of 50 mL to 200 mL was made, then:

$$\text{Lithium, mass \%} = (X)(200)/(100 W)(50) \quad (2)$$

9.2 Report the result as lithium content.

9.3 Calculate the sodium content of the grease as follows:

$$\text{Sodium, mass \%} = Y/100 W \quad (3)$$

where:

Y = sodium content of the water extract in mg/L sodium (see 8.7), and

W = mass of the grease taken, g.

Modify the formula if further dilution of the water extract was necessary as in 9.1.

9.4 Report the result as sodium content.

10. Precision and Bias

NOTE 2—The precision data were derived within the IP. The method has not as yet been cooperatively tested by ASTM.

10.1 The precision of this test method as determined by statistical examination of interlaboratory results is as follows:

10.1.1 *Lithium*:

10.1.1.1 *Repeatability*—The difference between two test results, obtained by the same operator with the same apparatus under constant operating conditions on identical test material, would in the long run, in the normal and correct operation of the test method, exceed the following values only in one case in twenty:

10.1.1.2 Lithium $0.014(x)^{2/5}$.

10.1.1.3 Sodium $0.029(x)^{2/5}$.

10.1.2 *Reproducibility*—The difference between two single and independent results obtained by different operators working in different laboratories on identical test material would, in the long run, in the normal and correct operation of the test method, exceed the following values only in one case in twenty:

10.1.2.1 Lithium $0.075(x)^{2/5}$.

10.1.2.2 Sodium $0.166(x)^{2/5}$, where *x* is the lower of two values.

NOTE 3—The applicable range of concentrations are 0 to 0.4 % mass/mass lithium and 0 to 8 % mass/mass sodium.

NOTE 4—These precision values have been obtained by statistical examination of interlaboratory test results by the Institute of Petroleum and were first published in 1966. They were obtained from the test results from nine laboratories using the following instruments:


No. of Laborato- ries	
6	"EEL" Flame Photometer.
2	SP 900 Unicam (modified).
1	H 700 Uvispek spectrophotometer (modified)

10.2 *Bias*—The bias of this test method cannot be determined because no suitable reference material is available.

NOTE 5—The values of these precision estimates for selected values of *x* are set out in the Table 1.

11. Keywords

11.1 flame photometer; lithium content; lubricating grease; sodium content; thickener

 **D 3340 – 98 (2003)**

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).