



Standard Specification for Shellac Varnishes¹

This standard is issued under the fixed designation D 360; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers shellac varnish consisting of a solution or “cut” of a specified type and grade of dry lac resin in specially denatured alcohol. Ninety-five percent (190 proof) ethyl alcohol, specially denatured according to Formula No. 1 of the Alcohol, Tobacco, and Firearms of the Treasury Dept., is the solvent most commonly used. However, other specially denatured alcohols and proprietary solvents are also used for this purpose.

2. Referenced Documents

- 2.1 *ASTM Standards:*
- D 29 Test Methods of Sampling and Testing Lac Resins²
- D 207 Specification for Dry Bleached Lac²
- D 237 Specification for Orange Shellac and Other Lacs²

3. Types, Grades, and Bodies

3.1 This specification covers two grades, A and B, of orange shellac varnish and two grades, regular and refined, of bleached lac varnish. Each type and grade may be furnished in very light, light, medium, heavy, very heavy, or extra heavy body varnish, as specified.

4. Color

4.1 The color of shellac varnish shall be no darker than the color of a standard varnish of the same nonvolatile matter content mutually agreed upon between the purchaser and the seller.

NOTE 1—Attention is called to the fact that the purchaser and the seller must agree upon one of the two methods for determining color appearing in Test Methods D 29.

5. Drying Time

5.1 Shellac varnish shall dry hard in 1 h. Shellac varnishes having a body greater than that for a light body varnish shall be thinned to the nonvolatile matter content of a light body varnish. Special conditions for this test may be made by mutual

agreement between the purchaser and the seller.

6. Body and Cut

6.1 The body and cut of the respective types and grades shall be based on the percent of nonvolatile matter and shall conform to the following minimum requirements:

	Nonvolatile Matter, min, %	
	Orange, Grades A and B	Bleached, Regular and Refined
Very light body (3-lb (1.4-kg) cut) varnish	28.5	28.0
Light body (4-lb (1.8-kg) cut) varnish	35.0	34.5
Medium body (4.5-lb (2.0-kg) cut) varnish	37.5	37.0
Heavy body (5-lb (2.3-kg) cut) varnish	40.0	39.5
Very heavy body (6-lb (2.7-kg) cut) varnish	44.0	43.5
Extra heavy body (8-lb (3.6-kg) cut) varnish	51.0	50.5

NOTE 2—The term “cut” is defined as the number of pounds of dry lac resin (containing only that amount of moisture acceptable for proper cutting with the solvent to ensure a satisfactory varnish) that were added to 1 gal (3.8 L) of specified solvent in manufacturing the varnish.

Allowance has, therefore, been made for 2 % maximum moisture and other volatile matter and 3 % insoluble matter in orange shellac, and for 6 % moisture and other volatile matter in bleached lac, in arriving at a minimum value. Varnishes of the above specified bodies or “cuts” should accordingly conform to the respective minimum requirements specified for nonvolatile matter.

7. Properties of Dry Lac

7.1 The nonvolatile matter in the varnish shall conform to the Properties section of Specification D 207 and Table 1 of Specification D 237.

8. Packaging and Marking

8.1 Shellac varnish shall be packaged in standard commercial containers of the type and size mutually agreed upon between the purchaser and the seller. The label of the container shall show the type, grade, body or cut, and date of manufacture of the varnish contained therein.

9. Test Methods

9.1 The sampling and methods of testing shall be conducted

¹ This specification is under the jurisdiction of the ASTM Committee D01 on Paint and Related Coatings, Materials and Applications, and is the direct responsibility of Subcommittee D01.33 on Polymers and Resins.

Current edition approved April 28, 1989. Published June 1989. Originally published as D 360 – 33. Last previous edition D 360 – 73 (1981).

² *Annual Book of ASTM Standards*, Vol 06.03.

in accordance with Test Methods D 29.

10. Keywords

10.1 denatured alcohol; dry lac resin; orange shellac; shellac varnish

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).