



Standard Specification for Zinc Hydroxy Phosphite Pigment¹

This standard is issued under the fixed designation D 4462; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers a zinc hydroxy phosphite pigment having the general formula $ZnHPO_3 \cdot [ZnO \cdot 2Zn(OH)_2]$.

2. Referenced Documents

2.1 ASTM Standards:

- D 185 Test Methods for Coarse Particles in Pigments, Pastes, and Paints²
- D 280 Test Methods for Hygroscopic Moisture (and Other Matter Volatile Under the Test Conditions) in Pigments²
- D 281 Test Method for Oil Absorption of Pigments by Spatula Rub-Out³
- D 4450 Test Method for Analysis of Zinc Hydroxy Phosphite Pigment²

3. Composition and Properties

3.1 The pigment shall consist of zinc hydroxy phosphite and shall conform to the requirements in Table 1.

3.2 The mass color of the dry pigment is white. The shade and tinting strength, when specified, shall be within mutually agreed upon limits of a reference sample acceptable by the purchaser and the seller as tested in an agreed test procedure.

4. Sampling

4.1 Two samples shall be taken at random from different packages from each lot, batch, day's pack, or other unit of

TABLE 1 Requirements for Zinc Hydroxy Phosphite Pigment

	Min	Max
Zinc (as ZnO), %	74.7	79.7
Phosphorus (as H_3PO_3), %	18.5	20.1
Moisture, %	...	1.25
Oil absorption, lb/100 lb pigment, %	15	22
Residue, No. 325 sieve, %	...	1.0

production in a shipment. When no markings distinguishing between units of production appear, samples shall be taken from different packages, in the ratio of two samples for each 10 000 lb (4545 kg), except that for shipments of less than 10 000 lb two samples shall be taken. At the option of the purchaser, the samples may be tested separately or after blending in equal quantities the samples from the same production unit to form a composite sample.

5. Test Methods

5.1 Tests shall be conducted in accordance with the following ASTM test methods. Test procedures not covered by ASTM test methods shall be mutually agreed upon between the purchaser and the seller.

5.2 *Chemical Analysis*—Test Method D 4450.

5.3 *Moisture Loss*—Determine the hygroscopic moisture loss by Method A of Test Methods D 280.

5.4 *Oil Absorption*—Test Method D 281.

5.5 *Sieve Residue*—Determine the residue on a No. 325 sieve in accordance with the Procedure for Insoluble Dry Pigments of Test Methods D 185.

6. Keywords

6.1 phosphorous acid; pigment; zinc; zinc hydroxy phosphite; zinc oxide

¹ This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved July 10, 2002. Published September 2002. Originally published as D 4462 - 85. Last previous edition D 4462 - 85 (1996)^{ε1}

² *Annual Book of ASTM Standards*, Vol 06.03.

³ *Annual Book of ASTM Standards*, Vol 06.01.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.



This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).