

AMERICAN SOCIETY FOR TESTING AND MATERIALS 100 Barr Harbor Dr., West Conshohocken, PA 19428 Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Test Method for Measuring Apparent pH of Water Insoluble Phenol-Formaldehyde Resins¹

This standard is issued under the fixed designation D 4613; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the measurement of the apparent pH of a water extract of an acetone solution of water insoluble phenol-formaldehyde resin.

1.2 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:

D 1193 Specification for Reagent Water²

E 70 Test Method for pH of Aqueous Solutions with the Glass $Electrode^3$

3. Summary of Test Method

3.1 Aqueous test solutions are generally used in determining pH. In this test method the resin is dissolved in acetone, water is added, and the apparent pH is measured with a pH meter.

4. Significance and Use

4.1 The hydrogen ion concentration (pH) is of critical importance due to its effect on the performance of the end product. The pH is widely used in quality control and process control.

5. Apparatus

5.1 *pH Meter*, complying with Test Method E 70.

5.2 Beaker, 250-mL.

5.3 Balance, accurate to 0.1 g.

6. Reagents

6.1 Purity of Reagents-Reagent grade chemicals shall be

² Annual Book of ASTM Standards, Vol 11.01.

used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁴ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 Water, conforming to Type II of Specification D 1193.

6.3 Acetone, reagent grade.

6.4 *pH Standard Solutions*—4, 7, 10 for standardization of pH meter.

7. Procedure

7.1 Standardize the pH meter with the 4, 7, or 10 standard buffer in the expected testing range.

7.2 Weigh a 10 ± 0.1 g specimen of the resin under test into a 250-mL beaker.

7.3 Add 40 mL of acetone and dissolve the specimen. Add 40 mL of water and stir for 5 min at room temperature. Allow the solution to settle for 1 min. Immerse the electrode into the solution (**Caution**: Keep undissolved resin away from electrode) and record the result.

7.4 Wash the electrode with acetone, followed by water until clean or until the pH meter returns to the standard buffer reading.

8. Report

8.1 Report the pH to 0.1 units.

9. Precision and Bias

9.1 The precision and bias for this test method have not been determined.

10. Keywords

10.1 pH; phenol-formaldehyde resins; water-insoluble

¹ This test method is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.33 on Polymers and Resins.

Current edition approved Sept. 26, 1986. Published November 1986.

³ Annual Book of ASTM Standards, Vol 15.05.

⁴ Reagent Chemicals, American Chemical Society Specifications, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see Analar Standards for Laboratory Chemicals, BDH Ltd., Poole, Dorset, U.K., and the United States Pharmacopeia and National Formulary, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

🚯 D 4613

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.