



Standard Specification for *n*-Butyl Acetate (All Grades)¹

This standard is issued under the fixed designation D 4615; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the various grades of *n*-butyl acetate suitable for use as solvents in paint and related coatings.

1.2 For specific hazard information and guidance, see the supplier's Material Safety Data Sheet for material listed in this specification.

2. Referenced Documents

2.1 ASTM Standards:

D 268 Guide for Sampling and Testing Volatile Solvents and Chemical Intermediates for Use in Paint and Related Coatings and Materials²

D 891 Test Methods for Specific Gravity, Apparent, of Liquid Industrial Chemicals³

D 1078 Test Method for Distillation Range of Volatile Organic Liquids²

D 1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)²

D 1296 Test Method for Odor of Volatile Solvents and Diluents²

D 1353 Test Method for Nonvolatile Matter in Volatile Solvents for Use in Paint, Varnish, Lacquer, and Related Products²

D 1364 Test Method for Water in Volatile Solvents (Karl Fischer Reagent Titration Method)²

D 1613 Test Method for Acidity in Volatile Solvents and Chemical Intermediates Used in Paint, Varnish, Lacquer, and Related Products²

D 3545 Test Method for Alcohol Content and Purity of Acetate Esters by Gas Chromatography²

D 4052 Test Method for Density and Relative Density of Liquid by Digital Density Meter⁴

E 1 Specification for ASTM Thermometers⁵

E 300 Practice for Sampling Industrial Chemicals⁶

2.2 *U.S. Federal Specification:*

PPP-C-2020 Chemicals, Liquid, Dry, and Paste: Packaging of⁷

3. Properties

3.1 *n*-Butyl acetate shall conform to one of the requirements of one of the grades in Table 1.

4. Sampling

4.1 The material shall be sampled in accordance with Practice E 300.

5. Test Methods

5.1 The properties enumerated in this specification shall be determined in accordance with the following ASTM methods:

5.1.1 *Purity and Alcohol Content*—Test Method D 3545.

5.1.2 *Apparent Specific Gravity*—Determine the apparent specific gravity by any convenient method that is accurate to the third decimal place, the temperature of both specimen and water being 20° or 25°C. (See Guide D 268, or Test Methods D 891 or D 4052.)

5.1.3 *Distillation Range*—Test Method D 1078, using an ASTM Solvents Distillation Thermometer 41C having a range from 98 to 152°C and conforming to the requirements in Specification E 1.

5.1.4 *Acidity*—Test Method D 1613.

5.1.5 *Water*—Test Method D 1364.

5.1.6 *Color*—Test Method D 1209.

5.1.7 *Nonvolatile Matter*—Test Method D 1353.

5.1.8 *Odor*—Test Method D 1296.

6. Packaging and Package Marking

6.1 Package size to be agreed upon between the purchaser and supplier.

6.2 Packaging shall conform to applicable carrier rules and regulations or when specified shall conform to Fed. Spec. PPP-C-2020.

7. Keywords

7.1 butyl acetate; ester; solvent

¹ This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved Feb. 15, 1995. Published April 1995. Originally published as D 4615 – 86. Last previous edition D 4615 – 90.

² *Annual Book of ASTM Standards*, Vol 06.04.

³ *Annual Book of ASTM Standards*, Vol 15.05.

⁴ *Annual Book of ASTM Standards*, Vol 05.02.

⁵ *Annual Book of ASTM Standards*, Vol 14.03.

⁶ *Annual Book of ASTM Standards*, Vol 15.05.

⁷ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094.

TABLE 1 Requirements for *n*-Butyl Acetate

Property	Grades			
	90–92	98	99.5	99.5U ^A
Purity, wt %, min	90–92	98.0	99.5	99.5
Alcohol, wt %, max	0.5	0.5
Color, Pt-Co units, max	10	10	10	10
Distillation Range, °C	118–128	120–128	124–129	124–129
Nonvolatile Matter, mg/100 mL, max	5	5	5	5
Odor ^B	Non-residual	Non-residual	Non-residual	Non-residual
Water, wt %, max	0.2	0.1	0.1	0.05 ^C
Acidity, wt %, max	0.01	0.01	0.01	0.01
Apparent Specific Gravity:				
20/20°C	0.874–0.876	0.880–0.883	0.880–0.883	0.880–0.883
25/25°C	0.870–0.872	0.876–0.879	0.876–0.879	0.876–0.879

^A Urethane grade material.

^B Test for odor is optional and should be agreed upon between the buyer and the seller.

^C Test method used to determine this value should be agreed upon between the buyer and the seller.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).