



Standard Test Methods for Chemical and Gravimetric Analysis of White and Yellow Thermoplastic Traffic Marking Containing Lead Chromate and Titanium Dioxide¹

This standard is issued under the fixed designation D 4797; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These test methods cover procedures for the chemical and gravimetric analysis of white and yellow thermoplastic traffic marking containing lead chromate and titanium dioxide pigment.

1.2 The analytical procedures appear in the following order:

	Sections
Percent Binder	10
Percent Glass Beads (Note 1)	11
Percent Titanium Dioxide	12
Percent Lead Chromate and Analysis of Chrome Yellow and Chrome Orange Pigments (Note 2)	13

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—Test for 1.50 glass spheres only.

NOTE 2—This modified analysis of chrome yellow and chrome orange pigments must be used because the heat resistant chrome yellows in the thermoplastic cannot be analyzed by Test Method D 126.

2. Referenced Documents

2.1 ASTM Standards:

- D 126 Test Methods for Analysis of Yellow, Orange, and Green Pigments Containing Lead Chromate and Chromium Oxide Green²
- D 883 Terminology Relating to Plastics³
- D 1193 Specification for Reagent Water⁴
- D 1394 Test Methods for Chemical Analysis of White Titanium Pigments²
- F 412 Terminology Relating to Plastic Piping Systems⁵

3. Terminology

3.1 *Definitions*—Definitions are in accordance with Terminology D 883 and F 412, unless otherwise indicated.

¹ These test methods are under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and are the direct responsibility of Subcommittee D01.44 on Traffic Coatings.

Current edition approved Oct. 31, 1988. Published December 1988.

² Annual Book of ASTM Standards, Vol 06.03.

³ Annual Book of ASTM Standards, Vol 08.01.

⁴ Annual Book of ASTM Standards, Vol 11.01.

⁵ Annual Book of ASTM Standards, Vol 08.04.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *ash*—the inorganic components of thermoplastic traffic marking including the pigment, glass spheres, and filler.

3.2.2 *binder*—the organic components of thermoplastic traffic marking that bind the pigments, glass spheres, and filler together as a unit.

3.2.3 *filler*—the inorganic components of thermoplastic traffic marking not including the pigments or glass spheres.

3.2.4 *pigment*—titanium dioxide and lead chromate colorants.

3.2.5 *thermoplastic*—See *thermoplastic traffic marking*.

3.2.6 *thermoplastic traffic marking*—a highly filled 100 % total solids highway marking system that when heated to a molten state can be extruded or sprayed onto a road surface and when cooled forms a solid durable delineator.

4. Summary of Test Method

4.1 The thermoplastic material is prepared for the described test methods by melting a sample to its application temperature under continuous agitation. The specimen is then poured into round patties on a clean tin plate or baking pan. The patties are then broken into pieces for ignition in a muffle furnace. The percent binder is calculated from the ashed specimen and the various tests for glass spheres, titanium dioxide, and lead chromate pigment are performed on the ashed residue. The tests for pigment type or glass spheres may be run on the same ashed specimen. Specimen selection and preparation are the same for each sample tested.

5. Significance and Use

5.1 The function of these test methods is to define the percent of binder, glass, titanium dioxide, and lead chromate present in the composition of the thermoplastic traffic marking as defined by the applicable specification for the manufacture of a specific thermoplastic traffic marking.

6. Apparatus

6.1 *Balance*, analytical, accurate to 0.1 mg.

6.2 *Buret*, 10 mL, 0.1-mL divisions.

6.3 *Buret*, 50 mL, 0.1-mL divisions.

6.4 *Crucibles*, 30 mL, porcelain.

6.5 *Desiccator*.

6.6 *Erlenmeyer flask*, 500 mL.

- 6.7 *Furnace (Muffle)*, capable of maintaining 1100°C.
 6.8 *Hot Plate*, capable of maintaining 537°C.
 6.9 *Jones Reductor*.
 6.10 *Mortar and Pestle*, glazed ceramic or other impervious type.
 6.11 *Oven*, capable of maintaining 260°C.
 6.12 *Sieve*, 3 in., 45- μ m (No. 325) (metal).

7. Reagents

7.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁶ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Type IV of Specification D 1193.

7.3 *Alcohol*—Ethyl alcohol 95 %.

7.4 *Potassium Chloride* (KCl).

7.5 *Potassium Hydroxide Solution*—Dissolve 50 g of potassium hydroxide (KOH) in 100 mL of freshly distilled water.

7.6 *Potassium Iodide* (KI).

7.7 *Potassium Permanganate Solution* (KMnO₄) (0.1N).

7.8 *Sodium Thiosulfate, Standard Solution*—(Na₂S₂O₃ · 5H₂O) (0.1 N).

7.9 *Starch (Soluble) Indicator Solution*—Dissolve 10 g of soluble starch in 1 L of deionized or distilled water.

7.10 *Hydrochloric Acid Solution* (HCl) (1 + 2).

7.11 *Hydrochloric Acid, Concentrated* (HCl).

8. Sampling

8.1 Samples may be obtained by an appropriate quartering or riffle sampling method where deemed necessary considering the physical form of the material.

9. Preparation of Specimens

9.1 Melt a sample of approximately 1000 g of thermoplastic traffic marking to 210 to 218°C under continuous agitation on a hot plate set at 537°C or stir every 15 min in an oven set at 260°C.

9.2 Flow the sample out on a smooth clean surface and allow it to cool to room temperature. Patties 1/8 in. (3 mm) thick will facilitate breaking up specimens for the described analysis.

9.3 Break the specimen into small pieces and weigh 10 g to the nearest 0.1 mg into a 30-mL weighed crucible.

9.4 Cover the crucible and place into a muffle furnace preheated to 540°C and ash for 1 h or until no carbonaceous materials remain.

9.5 Remove the crucible with the ashed remains of the specimen and place into a desiccator and cool to room temperature.

10. Percent Binder

10.1 Procedure:

10.1.1 Weigh the crucible and ash (see Section 9) to the nearest 0.1 mg and calculate the percent of organic binder *D* as follows:

$$D = [1 - (S/W)] \times 100 \quad (1)$$

where:

S = ashed weight of thermoplastic specimen, g, and

W = weight of thermoplastic specimen, g.

11. Percent Glass Beads

11.1 *Interferences*—Acid-insoluble fillers will affect the glass-sphere analysis and must be removed by some physical separation method or accounted for quantitatively, or both.

11.2 Procedure:

11.2.1 Weigh the crucible and ash (see Section 9) to 0.1 mg and calculate the percent ash.

11.2.2 After the ashed material has been weighed, transfer the ash to a mortar and pestle and grind with minimal pressure to reduce the ash to a fine grained consistency without crushing the beads. Carefully transfer the ashed contents into a 400-mL beaker.

11.2.3 Add to the ash approximately 150 mL of cold 1 + 2 HCl and stir occasionally until the effervescence has ceased completely.

11.2.4 Place the beaker on a hot plate preheated to approximately 260°C and boil for 20 min under continuous agitation to dissolve all acid-soluble filler pigments.

11.2.5 Remove the beaker from the hot plate, and while hot, immediately dilute the contents with 150 mL of cold water. Allow the beads to settle. Decant the water carefully so as not to lose any glass beads.

11.2.6 Continue diluting with 150-mL aliquots of water and decanting until the water is nearly clear. Then transfer the residue into a weighed 3-in. 45- μ m (No. 325) sieve and wash with 500 mL of cold water.

11.2.7 Dry the sides and the bottom of the sieve with a paper towel and dry for 1 h in a gravity oven preheated to 100°C.

11.2.8 Place the sieve in a desiccator and cool to room temperature. Weigh the sieve and glass beads to 0.1 mg and calculate the percent beads *G* as follows:

$$G = (B/W) \times 100 \quad (2)$$

where:

B = weight of the glass beads, g, and

W = weight of thermoplastic specimen, g.

12. Percent Titanium Dioxide

12.1 Procedure:

12.1.1 Weigh the crucible and ash (see Section 9) to 0.1 mg and calculate the percent of ash which is also equal to the percent filler (pigments and beads).

12.1.2 After weighing the above ashed materials, carefully transfer the ash to an agate or similar impervious-type mortar. Grind the ash to a consistent fine powder except for the glass beads. The pulverized ash must be stirred each time specimens are taken to weigh the prescribed amount for the analysis.

12.1.3 Weigh 1 \pm 0.1 g of ash for the titanium analysis.

⁶ "Reagent Chemicals, American Chemical Society Specifications," Am. Chemical Soc., Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see "Reagent Chemicals and Standards," by Joseph Rosin, D. Van Nostrand Co., Inc., New York, NY, and the "United States Pharmacopeia."

12.1.4 Proceed with the titanium analysis as described in Test Methods D 1394. The Jones Reductor or aluminum reduction method may be used.

12.1.5 At the end of the digestions described in Test Methods D 1394, filter the undigested materials through a 3-in. 45- μm (No. 325) sieve with hot water. This will prevent clogging of the Jones Reductor. This step is not necessary if the aluminum reduction method is used.

12.1.6 Calculate the percent of titanium dioxide (TiO_2) from the total ash weighed. The result gives the percent of TiO_2 in the total thermoplastic specimen.

12.1.7 Calculate the percent ash A as follows:

$$A = (S/W) \times 100 \quad (3)$$

where:

S = weight of ash, g, and

W = weight of thermoplastic specimen used, g.

12.1.8 Calculate the percent of total TiO_2 in the T based on percent ash:

$$T = 0.08 AMN/CS_a \quad (4)$$

where:

A = ash (pigment + filler + beads), %,

S_a = weight of ash used, g,

M = amount of 0.1 N potassium permanganate (KMnO_4) solution used, mL, (see the paragraph on titration with KMnO_4 solution of the Procedure section of the Jones Reductor Method of Test Methods D 1394),

N = normality of KMnO_4 used,

C = correction factor for TiO_2 pigment used (usually 1.0). This represents the purity of the pigment if specified, and

0.08 = weight of TiO_2 per 1 mL of 1 N KMnO_4 , g.

13. Percent Lead Chromate

13.1 Procedure:

13.1.1 Weigh the crucible and ash (see Section 9) to 0.1 mg and calculate the percent of ash.

13.1.2 After weighing the above ashed materials, carefully transfer the ash to an agate or similar impervious type mortar and grind the ash to a consistent fine powder except for the glass beads. The pulverized ash must be stirred when specimens are taken to weigh the prescribed amount for the analysis.

13.1.3 Weigh 1 ± 0.1 g of the ash for the lead chromate (PbCrO_4) analysis.

13.1.4 Analyze the dry ash as follows:

13.1.4.1 Transfer the ashed specimen to a 500-mL Erlenmeyer flask. Add 6 mL of the (KOH) solution (see 7.5) and 10 mL of distilled water. Heat until dissolved. Do not allow to dry. To the hot solution add 50 g of KCl. Dilute with water to 200 mL and swirl until dissolved. Add 16 mL of HCl slowly. Add 10 g of KI and titrate with the standard sodium thiosulfate solution (see 7.7) using the starch solution (see 7.8) as the indicator. Titrate to a green endpoint.

NOTE 3—A 10-mL buret may be used since the titrant required is small for most thermoplastic analysis.

13.1.5 Calculate the percent ash A as follows:

$$A = (S/W) \times 100 \quad (5)$$

where:

S = weight of gas, g, and

W = weight of the thermoplastic specimen used, g.

13.1.6 Calculate the percent of total PbCrO_4 in the sample (binder + filler) L based on percent ash as follows:

$$L = 0.1077 AMN/CS_a \quad (6)$$

where:

A = ash (pigment + filler + beads), %,

C = correction factor for PbCrO_4 pigment used (for example, 90 to 100 %, normally 1.0). This represents the purity of the pigment if specified,

M = amount of 0.1 N sodium thiosulfate solution used, mL,

N = normality of sodium thiosulfate used, and

S_a = weight of ash used, g.

14. Precision and Bias

14.1 No general statement of precision can be made because of lack of sufficient data at this time.

14.2 No statement of bias can be prepared for this test method since there is no absolute method for use as a basis for comparison.

15. Keywords

15.1 glass spheres (in traffic paint); lead chromate; titanium dioxide; thermoplastic traffic marking material

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.