



Standard Specification for Low Silicate Ethylene Glycol Base Engine Coolant for Heavy Duty Engines Requiring a Pre-Charge of Supplemental Coolant Additive (SCA)¹

This standard is issued under the fixed designation D 4985; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers the requirements for low silicate ethylene glycol base engine coolants for cooling systems of heavy-duty engines. When concentrates are used at 40 to 60 % concentration by volume in water, or when prediluted glycol base engine coolants (50 volume % minimum) are used without further dilution, they will function effectively to provide protection against corrosion, freezing to at least -37°C (-34°F), and boiling to at least 108°C (226°F).

NOTE 1—This specification is based on the knowledge of the performance of engine coolants prepared from new or virgin ingredients. Separate specifications exist (D 6210 and D 6211) for heavy-duty engine coolants which may be prepared from recycled or reprocessed used coolant or reprocessed industrial-source ethylene glycol.

1.2 Coolants meeting this specification require an initial charge of a supplemental coolant additive (SCA) and require regular maintenance doses of an SCA to continue the protection in certain operating heavy-duty engine cooling systems, particularly those of the wet cylinder liner-in-block design. The SCA additions are defined by and are the primary responsibility of the engine manufacturer or vehicle manufacturer. If they provide no instructions, follow the SCA supplier's recommended instructions.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 512 Test Methods for Chloride Ion in Water²

D 516 Test Method for Sulfate Ion in Water²

- D 1119 Test Method for Percent Ash Content of Engine Coolants and Antirusts³
- D 1120 Test Method for Boiling Point of Engine Coolants³
- D 1121 Test Method for Reserve Alkalinity of Engine Coolants and Antirusts³
- D 1122 Test Method for Density and Relative Density of Engine Coolant Concentrates and Engine Coolants by the Hydrometer³
- D 1123 Test Methods for Water in Engine Coolant Concentrate by the Karl Fischer Reagent Method³
- D 1126 Test Method for Hardness in Water²
- D 1177 Test Method for Freezing Point of Aqueous Engine Coolants³
- D 1193 Specification for Reagent Water²
- D 1287 Test Method for pH of Engine Coolants and Antirusts³
- D 1293 Test Methods for pH of Water²
- D 1384 Test Method for Corrosion Test for Engine Coolants in Glassware³
- D 1881 Test Method for Foaming Tendencies of Engine Coolants in Glassware³
- D 1882 Test Method for Effect of Cooling System Chemical Solutions on Organic Finishes for Automotive Vehicles³
- D 1888 Test Methods for Particulate and Dissolved Matter, Solids, or Residue in Water⁴
- D 2570 Test Method for Simulated Service Corrosion Testing of Engine Coolants³
- D 2809 Test Method for Cavitation Corrosion and Erosion-Corrosion Characteristics of Aluminum Pumps With Engine Coolants³
- D 3306 Specification for Glycol Base Engine Coolant for Automobile and Light-Duty Service³
- D 3634 Test Method for Trace Chloride Ion in Engine Coolants³
- D 4327 Test Method for Anions in Water by Chemically Suppressed Ion Chromatography²
- D 5827 Test Method for Determination of Chloride in Engine Coolant by Ion Chromatography³

¹ This specification is under the jurisdiction of ASTM Committee D15 on Engine Coolants and is the direct responsibility of Subcommittee D15.07 on Specifications. Current edition approved September 10, 2000. Published November 2000. Originally published as D 4985 – 89. Last previous edition D 4985 – 00.

² *Annual Book of ASTM Standards*, Vol 11.01.

³ *Annual Book of ASTM Standards*, Vol 15.05.

⁴ Discontinued—See 1990 *Annual Book of ASTM Standards*, Vol 11.01.

- D 5931 Test Method for Density and Relative Density of Engine Coolant Concentrates and Aqueous Engine Coolants by Digital Density Meter³
- D 6129 Test Method for Silicon in Engine Coolant Concentrates by Atomic Absorption Spectroscopy³
- D 6130 Test Method for the Determination of Silicon and Other Elements in Engine Coolant by Inductively Coupled Plasma-Atomic Emission Spectroscopy³
- D 6210 Specification for Fully Formulated Ethylene Glycol Base Engine Coolant for Heavy Duty Engines³
- D 6211 Specification for Fully Formulated Propylene Glycol Base Engine Coolant for Heavy Duty Engines³
- E 1177 Specification for Engine Coolant Grade Ethylene Glycol³

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *heavy duty engine*—a diesel, gasoline, or similarly fueled internal combustion engine, having operating characteristics of a long duty cycle at or near maximum rated conditions. Such engines are typically used in off-highway machinery for agriculture, mining, earth-moving, and construction; Class 5 to 8 over the road trucks and buses; high output stationary engine installations; and locomotive and marine installations. (See Specification D 3306 for coolant requirements for automobiles, vans, and pickup class trucks.)

3.1.2 *supplemental coolant additive (SCA)*—a material added to the cooling system of a heavy-duty engine to provide additional cavitation protection and corrosion inhibition and to minimize deposits on heat transfer surfaces.

4. General Requirements

4.1 Ethylene glycol base engine coolant concentrates or prediluted ethylene glycol base engine coolants shall be formulated with ethylene glycol meeting Specification D 1177, water, and shall contain suitable corrosion inhibitors, dye, and a foam suppressor. Other glycols, such as propylene and diethylene, may be included in concentrates up to a maximum of 15 % (7.5 % for prediluted coolants) if the physical and chemical properties in Table 1 are met.

4.2 All ethylene glycol base engine coolants shall conform to the general requirements in Table 2.

4.3 Prediluted coolants shall be prepared using deionized water that meets Type IV reagent water specifications (see Specification D 1193).

NOTE 2—Prediluted coolants are intended for direct addition to an engine cooling system with no further dilution.

This practice minimizes the formation of hard water scale and avoids the introduction of mineral components, such as chlorides and sulfates, which can increase the corrosion rate of aluminum and iron. The use of Type IV reagent water also minimizes interferences that may cause coolant instability or SCA compatibility problems.

4.4 When diluting engine coolant concentrates for actual service, municipal (treated) or a low-mineral content well water should be used (see Appendix X1, Table X1.1).

4.5 Diluted coolant concentrates or prediluted coolants, when mixed with SCA in accordance with the engine manu-

TABLE 1 Physical and Chemical Requirements

Property	Specific Values		ASTM Test Method
	Concentrate	Predilute	
Relative density, 15.5/15.5°C (60/60°F)	1.110 to 1.145	1.065 min	D 1122, D 5931
Freezing point, °C (°F): 50 vol % in DI water Undiluted	-37 (-34) max	-37 (-34) max	D 1177
Boiling point, ^A °C (°F): Undiluted 50 vol % in DI water	163 (325) min 108 (226) min	108 (226) min	D 1120
Ash content, mass %	5 max	2.5 max	D 1119
pH: 50 vol % in DI water Undiluted	7.5 to 11	7.5 to 11	D 1287
Reserve alkalinity, mL	report ^B	report ^B	D 1121
Water, mass %	5 max	not applicable	D 1123
Chloride ion, ppm	25 max	25 max	D 3634, D 5827
Silicon, ppm	250 max	125 max	D 6129, D 6130
Effect on engine or vehicle finish	no effect	no effect	D 1882 ^C

^ASome precipitate may be observed at the end of the test method. This should not be cause for rejection.

^BValue as agreed upon between the supplier and the customer.

^CCurrently, many heavy-duty engine manufacturers and vehicle manufacturers that use these engines prepare test panels using the specific paint finishes employed on their actual products. Coolant suppliers and equipment builders should agree on the exact test procedures and acceptance criteria on an individual case basis.

TABLE 2 General Requirements

Property	Specific Values	ASTM Test Method
Color	distinctive	...
Effect on nonmetals	no adverse effect	under consideration

facturer’s recommendations and those on the product label, shall be suitable for use in a properly maintained cooling system in normal service for a minimum of one year (see Appendix X1).

5. Detailed Requirements

5.1 Ethylene glycol base engine coolant concentrate shall conform to the physical and chemical requirements in Table 1 and the performance requirements in Table 3.

5.2 Prediluted aqueous ethylene glycol base engine coolants (50 volume % minimum) shall conform to the physical and chemical property requirements in Table 1. The requirements listed in Table 1 for prediluted coolants are prescribed for the coolant as packaged, without further dilution or adjustment.

5.3 The freezing point of prediluted aqueous ethylene glycol base engine coolants, as packaged, shall be -37°C (-34°F) or lower.

5.4 If necessary, adjust the freezing point of the prediluted aqueous coolant to -37°C (-34°F) with deionized water before proceeding with performance testing.

5.5 Prediluted aqueous ethylene glycol base engine coolants shall conform to the performance requirements prescribed in Table 3, after any needed concentration adjustment.

TABLE 3 Performance Requirements^A

Property	Specific Values	ASTM Test Method	Test Solution Concentration, vol % Glycol
Corrosion in glassware		D 1384 ^B	33
Weight loss, mg/specimen:			
copper	10 max		
solder	30 max		
brass	10 max		
steel	10 max		
cast iron	10 max		
aluminum	30 max		
Simulated service test		D 2570 ^C	44
weight loss, mg/specimen:			
copper	20 max		
solder	60 max		
brass	20 max		
steel	20 max		
cast iron	20 max		
aluminum	60 max		
Foaming:		D 1881 ^D	33
Volume, mL	150 max		
Break time, s	5 max		
Cavitation-Erosion	8 min	D 2809 ^E	17
Rating for pitting, cavitation, and erosion of the water pump			

^AFor engine coolant concentrates, test solutions shall be prepared in accordance with the directions provided in the individual ASTM test methods. For prediluted engine coolants, prepare the test solutions using the directions provided in Footnotes B through E.

^BFor prediluted coolants, prepare the test solution by mixing 67 volume % of the adjusted (see 4.5) prediluted product with 33 volume % ASTM Type IV reagent water. Add 99 mg of sodium sulfate, 110 mg of sodium chloride, and 92 mg of sodium bicarbonate per litre of test solution.

^CFor prediluted coolants, prepare the test solution by mixing 88 volume % of the adjusted (see 4.5) prediluted product with 12 volume % ASTM Type IV reagent water. Add 83 mg of sodium sulfate, 92 mg of sodium chloride, and 77 mg of sodium bicarbonate per litre of test solution.

^DFor prediluted coolants, prepare the test solution by mixing 67 volume % of the adjusted (see 4.5) prediluted product with 33 volume % ASTM Type IV reagent water.

^EFor prediluted coolants, prepare the test solution by mixing 33 volume % of the adjusted (see 4.5) prediluted product with 67 volume % ASTM Type IV reagent water. Add 123 mg of sodium sulfate, 137 mg of sodium chloride, and 115 mg of sodium bicarbonate per litre of test solution.

6. Keywords

6.1 coolant requiring SCA pre-charge; engine coolant; ethylene glycol; heavy duty engine coolant; heavy duty engine

service; low silicate engine coolant; prediluted

APPENDIX

(Nonmandatory Information)

X1. COOLANT MAINTENANCE FOR HEAVY DUTY ENGINES

X1.1 *Engine Coolant*—Cooling system fill for a heavy-duty engine consists either of water, coolant concentrate (antifreeze) and supplemental coolant additive (SCA), or prediluted engine coolant and SCA.

X1.1.1 *Water:*

X1.1.1.1 Water quality affects the efficiency of coolant additives. When untreated, all water is corrosive. Water having a high mineral content or corrosive materials is unfit for cooling system use.

X1.1.1.2 When preparing solutions for actual service, the water should be of such quality that it does not contain excessive solids, hardness, salts, sulfates, or chlorides. Contact your local water department, responsible government agency, or submit a water sample for analysis if there is any question about water quality. Follow the specific water quality recommendations of the engine or vehicle manufacturer or responsible servicing organization. In the absence of such recommendations, see Table X1.1.

TABLE X1.1 Suggested Water Quality Limits^A

Property	Specific Values	ASTM Test Method
Total solids, ppm (grains/gal)	340 (20) max	D 1888
Total hardness, ppm (grains/gal)	170 (10) max	D 1126
Chloride (Cl ⁻), ppm (grains/gal)	40 (2.4) max	D 512, D 4327
Sulfate (SO ₄ ⁻²), ppm (grains/gal)	100 (5.9) max	D 516, D 4327
pH	5.5 to 9.0	D 1293

^ASuggested by the Engine Manufacturers' Association coolants subcommittee based on a survey of service recommendations of North American heavy duty diesel engine manufacturers.

X1.1.2 Coolant Concentrate—Ethylene glycol-base concentrate meeting this specification is recommended for freeze, boil-over, and corrosion protection. Maintain coolant concentrate (anti-freeze) concentration between 40 % (freeze protection to -24°C (-12°F)) and 60 % (freeze protection to -52°C (-62°F)), depending on operating environment.

X1.1.3 Prediluted Engine Coolant—Prediluted ethylene glycol base coolant (50 volume % antifreeze minimum) meeting this specification is recommended for freeze, boil-over, and corrosion protection. This product, as packaged, will provide freeze protection to -37°C (-34°F). Further dilution is not recommended. However, if circumstances require addition and prediluted aqueous engine coolant is not available, use an ethylene glycol base coolant concentrate diluted to 50 volume % with water of at least the quality outlined in Table X1.1

X1.1.4 Supplemental Coolant Additive (SCA)—The SCAs are used to provide additional protection against deposits, corrosion, and pitting which may not be provided by the additives in coolant concentrates or prediluted engine coolants. The SCAs also extend the life of the coolant by adding to and replenishing the additives that deplete during normal operation. SCAs, however, do not extend the freeze protection provided by the coolant concentrate or the prediluted coolant.

X1.1.5 Nonvirgin Coolants:

X1.1.5.1 Current coolant product specifications are based on performance experience developed when these products are prepared from new or virgin ingredients. Therefore, this specification does not take into account the effect(s), if any, of any elements or chemical compounds that may have been added or may be residual, if the coolant product is prepared from recycled or reprocessed used coolant, or reprocessed reused industrial sourced glycols.

X1.1.5.2 ASTM Committee D15 has investigated the effects of potential contaminants and has established specifications for recycled and reformulated coolants.

X1.2 Coolant Maintenance Recommendations:

X1.2.1 If any of the following recommendations differ, follow the engine or vehicle manufacturer's recommendations.

X1.2.2 Replace coolant at service intervals recommended by the engine manufacturer.

X1.2.3 Follow the engine or vehicle manufacturer's recommendations for SCA pre-charging of the cooling system after draining and flushing.

X1.2.4 Use water that does not contain excessive solids, hardness, chloride, or sulfate.

X1.2.5 Use accurate, reliable equipment such as a refractometer to measure coolant concentrate levels for freeze protection.

X1.2.6 Use the SCA manufacturer's recommended test kit when testing the coolant for proper SCA concentration. Test kits shall indicate the degree of liner pitting protection present in the coolant. A service coolant analyses program can also be used to ensure proper maintenance of the engine or vehicle cooling system. Such analyses programs are available commercially.

X1.2.7 Check freezing point at two different levels when coolant concentrate and water is premixed and stored in bulk or drums to ensure mixing is complete before use.

X1.2.8 Use coolant mixed at the desired proportions for make-up.

X1.2.9 Use SCAs at recommended dosage to control deposits, corrosion, and pitting.

X1.2.10 Periodically check bulk premixed coolant storage tanks for separation of chemicals and contamination.

X1.2.11 DO NOT add undiluted coolant concentrate as make-up coolant.

X1.2.12 DO NOT add plain water as make-up coolant.

X1.2.13 DO NOT substitute pre-charge coolant filters for service filters; this will result in over treatment, (pre-charge filters contain more SCA than maintenance filters).

X1.2.14 DO NOT exceed 60 % coolant concentrate. A coolant concentrate level greater than 68 % actually reduces freeze protection in ethylene glycol base coolants. The maximum recommended coolant concentrate level is 60 % which provides freeze protection to -52°C (-62°F). Coolants containing 50 % coolant concentrate, or prediluted coolants (50 volume % minimum), provide freeze protection to -37°C (-34°F).

X1.2.15 DO NOT exceed the recommended dosage of SCA or the recommended concentrate of coolant concentrate. Over concentration can result in plugged radiators, heater cores, and charge air coolers. Over concentration can also cause water pump seal leaks.

X1.2.16 DO NOT reuse coolant that has been drained from a vehicle where over concentration of coolant concentrate or over concentration of supplemental coolant additives has occurred, where the coolant is over one-year old, or where the container is dirty.

X1.2.17 DO NOT pre-charge the cooling system with SCA if the coolant is drained and reused.

X1.2.18 DO NOT use soluble oil additives.

X1.2.19 DO NOT use methyl alcohol or methoxy propanol base coolant concentrates.

X1.2.20 DO NOT use antileak additives if engine cooling system is equipped with a coolant filter, as this may plug the filter element. For all other cooling systems, follow the recommendations of the engine or vehicle manufacturer.

X1.3 Prediluted Engine Coolants:

X1.3.1 It is recommended that prediluted engine coolant products meeting this specification have the following information on the package label:

X1.3.1.1 Prediluted engine coolant,

X1.3.1.2 Do not add water,

X1.3.1.3 Meets ASTM Specification D 4985, and

X1.3.1.4 Caution—The freezing point of the new coolant is dependent on the amount of old coolant remaining in the

 **D 4985**

cooling system at the time of filling. To determine the freezing point accurately, run the engine one hour or until the new and old coolants have mixed adequately.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).