



Standard Practice for Classifying Emulsified Recycling Agents¹

This standard is issued under the fixed designation D 5505; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice identifies emulsified petroleum products that may be used as recycling agents in recycled mixes. These materials are classified by viscosity or by low temperature penetration after aging.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to consult and establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.3 This practice addresses emulsified materials designed specifically for use in recycling. The use of emulsified materials for recycling shall not be limited to this practice. For instance, the emulsions specified in Specifications D 977 and D 2397 may be used.

2. Referenced Documents

2.1 ASTM Standards:

- D 5 Test Method for Penetration of Bituminous Materials²
- D 70 Test Method for Specific Gravity and Density of Semi-Solid Bituminous Materials²
- D 140 Practice for Sampling Bituminous Materials²
- D 244 Test Methods for Emulsified Asphalts²
- D 977 Specification for Emulsified Asphalt²
- D 1754 Test Method for Effect of Heat and Air on Asphaltic Materials (Thin Film Oven Test)²
- D 2007 Test Method for Characteristic Groups in Rubber Extender and Processing Oils and Other Petroleum-Derived Oils by the Clay-Gel Absorption Chromatographic Method³
- D 2042 Test Method for Solubility of Asphalt Materials in Trichloroethylene²
- D 2170 Test Method for Kinematic Viscosity of Asphalts (Bitumens)²
- D 2397 Specification for Cationic Emulsified Asphalt²
- D 2872 Test Method for Effect of Heat and Air on a Moving

Film of Asphalt (Rolling Thin-Film Oven Test)²

3. Significance and Use

3.1 Recycling of deteriorated asphalt pavements is being used as a routine method of maintenance and rehabilitation. Utilization of existing materials as the major component of this procedure may yield benefits in quality, economy, and preservation of natural resources. Recycling takes many forms; hot, cold, in-situ, central plant and surface. This practice may be used for various recycling methods.

4. Classification

4.1 This practice describes emulsified recycling (ER) agents as belonging to three groups; ER-1, ER-2, and ER-3 as shown in Table 1. The range of recycling methods demands several emulsified recycling agents. The groups should provide adequate freedom of selection for most recycling methods.

4.1.1 ER-1 is a material whose main function is to rejuvenate aged asphalt. The material is a petroleum derivative, and highly compatible with asphalts. It is classified by viscosity.

4.1.2 ER-2 and ER-3 are materials that combine rejuvenators and asphalt components in one emulsion. These soft residues are classified by low temperature penetration after aging. They are typically used in recycling where there is an increased demand for bitumen as when new aggregates are added, or where immediate cohesiveness is desired.

4.2 The choice of ER will be determined by the consistency of the binder in the aged pavement, the methods of recycling planned, the amount, if any, of new aggregates, and other design needs.

5. Properties

5.1 All emulsified recycling agents shall be homogenous, free flowing at pumping temperature, and shall conform to the requirements of Table 1.

5.2 Emulsified recycling agent residue should be combined with aged asphalts and evaluated to determine proper ER selection and to determine quantity of treatment. Resulting binder properties shall be judged suitable for the intended use.

6. Sampling

- 6.1 Carry out sampling in accordance with Practice D 140.
- 6.2 Store samples in new, clean, airtight sealed containers as

¹ This practice is under the jurisdiction of ASTM Committee D-4 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.41 on Emulsified Asphalt Specifications.

Current edition approved Aug. 10, 1997. Published April 1998. Originally published as D 5505-94. Last previous edition D 5505-94.

² *Annual Book of ASTM Standards*, Vol 04.03.

³ *Annual Book of ASTM Standards*, Vol 05.01.

TABLE 1 Specifications for Emulsified Recycling Agents

Tests	Test Method	ER-1		ER-2		ER-3	
		min	max	min	max	min	max
On emulsion							
Viscosity, 50°C, SFs	D 244	100		20	450	20	450
Sieve, %	D 244	0.1		0.1		0.1	
Storage stability, 24 h, %	D 244	1.5		1.5		1.5	
Residue, by distillation, %	D 244	65		65		65	
Dilution			report ^A				
Specific gravity	D 70		report		report		report
Compatibility ^B	varies		report		report		report
On residue from distillation							
Kinematic Viscosity, 60°C, mm ² /s	D 2170	50	200				
Saturates, %	D 2007		30		30		30
Solubility in Tri-chloroethylene	D 2042	97.5		97.5		97.5	
On residue from distillation after RTFO ^C							
Penetration, 4°C, 50 g, 5 s	D 5			75	200	5	75
RTFO, weight change, %	D 2872	4		4		4	

^A ER-1 shall be certified for dilution with potable water.

^B This specification allows a variety of emulsions, including high-float and cationic emulsions. The engineer should take the steps necessary to keep incompatible materials from co-mingling in tanks or other vessels. It would be prudent to have the chemical nature (float test for high float emulsions, particle charge test for cationic emulsions, or other tests as necessary) certified by the supplier.

^C RTFO shall be the standard. When approved by the engineer, the Thin Film Oven Test (Test Method D 1754) may be substituted for compliance testing.

specified in Practice D 140 at a temperature not less than 4°C until tested.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

7. Keywords

7.1 emulsified recycling agent; emulsions; recycling