



Standard Test Methods for Specific Gravity of Coating Powders¹

This standard is issued under the fixed designation D 5965; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope *

1.1 These test methods cover three procedures for determining the specific gravity (see definition) of coating powders, as follows:

TEST METHOD A—For Testing Coating Powders, Excluding Metallics
TEST METHOD B—For Tests Requiring Greater Precision than Test Method A, Including Metallics, Using Helium Pycnometry
TEST METHOD C—For Theoretical Calculation Based on Raw Material Specific Gravities

1.2 Test Method A can be used as a less expensive method with reduced accuracy for determining the specific gravity of coating powders, excluding metallics.

1.3 The ideal gas law forms the basis for all calculations used in the Test Method B determination of density of coating powders.

1.4 Test Method B includes procedures that provided acceptable results for samples analyzed during round robin testing.

1.5 Test Method B uses SI units as standard. State all numerical values in terms of SI units unless specific instrumentation software reports surface area using alternate units. Many instruments report density as g/cm^3 , instead of using SI units (kg/m^3).

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 3924 Specification for Standard Environment for Conditioning and Testing Paint, Varnishes, Lacquers, and Related Materials²

¹ These test methods are under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and are the direct responsibility of Subcommittee D01.51 on Powder Coatings.

Current edition approved Jan. 10, 2002. Published March 2002. Originally published as D 5965 - 96. Last previous edition D 5965 - 96.

² *Annual Book of ASTM Standards*, Vol 06.01.

D 5382 Guide to Evaluation of Optical Properties of Powder Coatings³

E 691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method⁴

3. Terminology

3.1 Definitions:

3.1.1 Definitions 3.1.1 and 3.1.3 are from Guide D 5382.

3.1.2 *coating powders*—finely divided particles of resin, either thermoplastic or thermosetting, generally incorporating pigments, fillers, and additives and remaining finely divided during storage under suitable conditions, which, after fusing and possibly curing, give a continuous film.

3.1.3 *meniscus*—curved upper surface of a liquid column that is concave when the containing walls are wetted by the liquid.

3.1.4 *powder coatings*—coatings which are protective or decorative, or both, formed by the application of a coating powder to a substrate and fused into continuous films by the application of heat or radiant energy.

3.1.5 *pycnometer*—instrument designed to measure the volume of solid materials using Archimedes' principle of fluid displacement. The displaced fluid is a helium gas.

3.1.6 *specific gravity*—(1) strict definition: the density of a substance relative to that of water. (2) practical, as used in this test method—The numerical value of the density when the latter is expressed in grams per millilitre.

4. Significance and Use

4.1 Test Method A is a less expensive method of determining specific gravity of coating powders, excluding metallics, that produced less precise results than Test Method B.

4.2 Test Method B provides better precision at higher cost and includes metallics, although different models produced different grand averages for each of the three samples tested.

4.3 Test Method C is commonly used by the powder coating industry to estimate the coverage of a powder coating at a given thickness, using the theoretical specific gravity calculated from those of the raw materials.

³ *Annual Book of ASTM Standards*, Vol 06.02.

⁴ *Annual Book of ASTM Standards*, Vol 14.02.

*A Summary of Changes section appears at the end of this standard.

5. Reagents

5.1 *Purity*—Wetting vehicles should be of reagent grades.

5.2 *Helium*—Shall be understood to mean high purity of commercial grade.

6. Conditioning

6.1 These tests should be standardized at $73.5 \pm 3.5^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) and relative humidity of $50 \pm 5\%$ for the two methods in compliance with Specification D 3924.

TEST METHOD A—FOR TESTING POWDER COATINGS, EXCLUDING METALLICS

7. Apparatus and Materials

7.1 *Volumetric Flask*—Calibrated narrow-necked glass type, having a 50-mL capacity.

7.2 *Balance*—A calibrated laboratory balance having a ± 0.001 g-accuracy. A less accurate balance can be used with a relative effect on the results.

7.3 *Coating Powder*—Weighed to 15 g, within a ± 0.01 g-accuracy.

7.4 *Immersion Liquid*—Hexane was found to be a good wetting vehicle for the epoxy and polyester coatings used in the round robin for the testing of repeatability and reproducibility.

7.5 *Glass Funnel*—Designed to fit within the neck of the volumetric flask.

7.6 *Polished Round-Bottom Glass Rods*— For dispersing powder.

7.7 *Squeeze Bottle*—Suitable for containing and dispensing wetting vehicle.

8. Hazards

8.1 Exercise care in handling all wetting vehicles. Make sure that personal equipment includes protective gloves, glasses, and clothing. Perform test method using wetting vehicles in a solvent hood.

9. Standardization

9.1 Weigh the empty, clean volumetric flask. Record this weight as *WF*.

9.2 The density of the wetting vehicle, recorded as *DL*, can be determined by adding exactly 50 mL of wetting vehicle to the previously weighed flask and reweighing. Record this weight as *WFL*. Calculate the density of the wetting vehicle (*DL*) as follows:

$$DL = \frac{(WFL - WF)}{50 \text{ mL}} \quad (1)$$

10. Procedure

10.1 Weigh the 50-mL volumetric flask. Record this weight as *WF*. Add 15 g of powder to the clean, dry, weighed flask and accurately reweigh. Record this weight as *WFP*. Add enough wetting vehicle to cover the powder and gently swirl until the powder is completely wet.

10.2 The removal of entrapped air has a significant effect on the accuracy of the results. Care should be taken to insure wetting out of the powder is complete. When necessary, stir the powder with a polished round-bottom glass rod until com-

pletely covered by the wetting vehicle. Wash the rod with wetting vehicle, adding the washings to the flask without exceeding the 50-mL calibration mark.

10.3 Add additional wetting vehicle up to the 50-mL mark. Make sure that the bottom of the meniscus is aligned at eye level with the line on the front and back of the flask neck. This addition of wetting vehicle can be done with a squeeze bottle in a manner to wash any residual powder from the neck of the flask. Reweigh and record this weight as *WFPL*.

10.4 Multiple volumetric flasks can be used in rotation to reduce cleaning and complete drying time.

10.5 **Immediately** clean the flask after each test to increase the ease with which this is accomplished. Each flask shall be completely clean and dry before proceeding to the next test.

11. Calculation

11.1 Calculate the density of the powder (*DP*) as follows:

$$DP = \frac{WFP - WF}{50 \text{ mL} - \frac{WFPL - WF}{DL}} = \frac{\text{numerator}}{\text{denominator}} \quad (2)$$

where:

WFP = weight of flask and powder,

WF = weight of flask,

WFPL = weight of flask, powder, and wetting vehicle,

DL = density of wetting vehicle, and

DP = specific gravity of powder.

11.2 An example, using hexane, would be as follows:

$$DP = \frac{50.545 \text{ g} - 36.581 \text{ g}}{50 \text{ mL} - \frac{77.200 \text{ g} - 50.545 \text{ g}}{0.663 \text{ g/mL}}} = \frac{13.964}{9.796} = 1.42 \text{ specific gravity} \quad (3)$$

where:

WFP = 50.545 g,

WF = 36.581 g,

WFPL = 77.200 g,

DL = 0.663 g/mL, and

DP = unknown.

12. Report

12.1 Report the following information:

12.1.1 Use duplicate determinations with the average reported to two significant figures to the right of the decimal.

12.1.2 Report the complete sample identification and the wetting vehicle used to determine the specific gravity.

13. Precision and Bias ⁵

13.1 *Precision*—The average of duplicate determinations by this test method should not differ by more than 0.025 using a balance with 0.0001 significant figures or 0.04 using a balance with 0.001 significant figures.

13.2 *Bias*—Bias has not been determined.

⁵ Supporting data are available from ASTM International Headquarters. Request RR:D01-1100.

**TEST METHOD B—FOR TESTS REQUIRING
GREATER PRECISION THAN TEST METHOD A,
INCLUDING METALLICS, USING HELIUM
PYCNOMETRY**

14. Apparatus and Materials

14.1 *Commercial Pycnometer Instruments*, available from several manufacturers for the measurement of skeletal volume by gas displacement. Some instruments perform calculations of volume or density, or both, upon completion of the analysis. Others require manual calculation of skeletal volume and density.

14.2 *Analytical Balance*, having a ± 0.0001 -g accuracy.

15. Sampling

15.1 It is important that the sample being analyzed represent the larger bulk from which it is taken. The bulk sample should be homogeneous before any sampling takes place.

16. Calibration and Standardization

16.1 Follow manufacturer's instructions for calibration and operational verification of the pycnometer and analytical balance.

17. Outgassing

17.1 Weigh the clean, empty sample holder to the nearest 0.1 mg. Record the empty holder weight.

17.2 Add representative sample to the empty sample holder. The sample quantity should be sufficient to satisfy the minimum skeletal volume as required by the manufacturer. Weigh and record the weight of the sample and sample holder.

NOTE 1—Move to the Procedure Section if the sample is to be outgassed in the pycnometer at the time of analysis.

17.3 Place prepared sample holder in outgassing device.

17.4 Program outgassing device for initial outgassing temperature. Increase temperature as appropriate for the sample. Allow sample to continue to outgas until prescribed vacuum level is achieved or prescribed outgassing time, or both.

17.5 Reduce the temperature of the outgassing device to ambient. Remove the sample holder.

17.6 Weigh the sample holder to the nearest milligram to obtain the sample and holder weight. Subtract the empty sample holder weight determined in 16.1 to obtain the outgassed sample weight. Record the calculated weight.

18. Procedure

18.1 Place the filled sample holder in the pycnometer and close the sample chamber.

18.2 *Automated Instruments Only*—Select, or input, the desired analysis and report parameters. Include the outgassing parameters if the sample preparation is performed as a part of the sample analysis. If necessary, input the outgassing sample weight. The final weight should be determined and entered after the analysis. Determine the skeletal volume a minimum of five times.

18.3 *Manually Operated Instruments*—Collect three to five sets of analysis data according to the manufacturer's recommended procedure for maximum accuracy and precision.

18.4 When the analysis has finished, remove the sample holder. Weigh the holder to the nearest 0.1 mg. Record the final holder and sample weight. Subtract the empty holder weight recorded in 16.1 to obtain the final sample weight.

18.5 *Automated Instruments Only*—Input the final sample weight. Generate the final sample report.

19. Calculations

19.1 *Automated Instruments Only*—Have software that automatically calculates the results for the chosen reports using the final weight input in 16.5.

19.2 *Manually Operated Instruments*—Calculate the skeletal volume using collected data according to the manufacturer's instructions. Use the final sample weight from 16.4 to calculate skeletal densities. Calculate the average and standard deviation for skeletal volume and density in accordance with Practice E 691.

20. Report

20.1 Report the following information:

20.1.1 Complete sample identification and measured skeletal volumes, statistics, and density determined. Note any units used other than standard.

20.1.2 Analysis gas type used.

20.1.3 Sampling outgassing method, including total time and outgassing temperature(s).

**TEST METHOD C—FOR THEORETICAL
CALCULATION BASED ON RAW MATERIAL
SPECIFIC GRAVITIES**

21. Calculations

21.1 *To Calculate the Theoretical Specific Gravity of a Coating Powder When the Formula is Known*—Divide the amount of each raw material (*RM*) by its specific gravity. Add the raw material amounts together and divide by the sum of the resulting values for all of the raw materials in the subject powder. The product of this calculation shall be the theoretical specific gravity of the coating powder, as follows:

$$\text{Theoretical specific gravity} = \frac{\text{grand total of amounts (RM1 through RM6)}}{\text{sum of resulting values (RM1 through RM6)}} \quad (4)$$

where:

<i>RM1</i> amount divided by specific gravity	=	<i>RM1</i> resulting value
<i>RM2</i> amount divided by specific gravity	=	<i>RM2</i> resulting value
<i>RM3</i> amount divided by specific gravity	=	<i>RM3</i> resulting value
<i>RM4</i> amount divided by specific gravity	=	<i>RM4</i> resulting value
<i>RM5</i> amount divided by specific gravity	=	<i>RM5</i> resulting value
<i>RM6</i> amount divided by specific gravity	=	<i>RM6</i> resulting value

Grand total Sum of resulting values

21.2 Report the powder specific gravity.

22. Precision and Bias ⁵

22.1 Precision and bias of the procedures in Test Methods A

and B for measuring the specific gravity of coating powders has not been determined because the minimum number of laboratories required by Practice E 691 was not met. An interlaboratory study was conducted by four laboratories to determine the specific gravity of two coating powders using Test Method A and three coating powders using Test Method B.

23. Keywords

23.1 coating powders; density; metallics; powder coatings; pycnometer; specific gravity

SUMMARY OF CHANGES

Committee D01 has identified the location of selected changes to this standard since the last issue (D 5965 - 96) that may impact the use of this standard.

Minor changes to:

- (1) Reference to hazard statement was deleted from 1.6.
- (2) Coating powders and powder coating definitions were revised in Section 3.

(3) Helium purity was revised in 5.2

(4) Paragraph 14.1 was revised.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).