



Standard Specification for Magnesium Silicate Pigment (Talc)¹

This standard is issued under the fixed designation D 605; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

^{ε1} NOTE—Keywords and unit of measurement statement were added editorially in July 1996.

1. Scope

1.1 This specification covers pigments that consist substantially of natural hydrous magnesium silicate, and is restricted to those minerals that conform to the chemical limits prescribed herein and can be suitably processed to what is commercially known as paint pigment quality.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The following hazard caveat applies to the test method portion of this specification only. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

- 2.1 *ASTM Standards:*
 - D 280 Test Methods for Hygroscopic Moisture (and Other Matter Volatile Under the Test Conditions) in Pigments²
 - D 281 Test Method for Oil Absorption of Pigments by Spatula Rub-Out³
 - D 562 Test Method for Consistency of Paints Using the Stormer Viscometer³
 - D 717 Test Methods for Analysis of Magnesium Silicate Pigment²
 - D 1208 Test Methods for Common Properties of Certain Pigments²
 - D 1210 Test Method for Fineness of Dispersion of Pigment-Vehicle Systems³

3. Composition and Properties

3.1 The pigment shall be made by grinding or otherwise

¹ This specification is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications, and is the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved June 25, 1982. Published August 1982. Originally published as D 605 – 41 T. Last previous edition D 605 – 69 (1976).

² *Annual Book of ASTM Standards*, Vol 06.03.

³ *Annual Book of ASTM Standards*, Vol 06.01.

processing natural, hydrous magnesium silicate and shall conform to the following requirements:

	Weight %	
	min	max
Combined magnesium and calcium silicates (MgO plus SiO ₂ plus CaO)	88	...
Calcium oxide (CaO)	...	10
Aluminum and iron oxides (R ₂ O ₃)	...	6
Loss on ignition	...	7
Moisture and other volatile material	...	1

3.2 *Color*—The color shall be equal, within agreed upon tolerances, to that of a reference sample agreed upon between the purchaser and the seller.

3.3 *Coarse Particles*—The pigment shall contain no more than 2 % of coarse particles, retained on a 45-μm (No. 325) sieve except as may be agreed upon between the purchaser and the seller.

3.4 *Water-Soluble Matter*—The pigment shall contain no more than 1 % water-soluble matter except as may be agreed upon between the purchaser and the seller.

3.5 *Oil Absorption*—The oil absorption shall be equal, within agreed upon tolerances, to that of a reference sample agreed upon between the purchaser and the seller.

3.6 *Consistency*—When consistency is included in the purchaser's specification, it shall be equal, within agreed upon tolerances, to that of a reference sample agreed upon between the purchaser and the seller.

3.7 *Fineness*—The paint fineness shall be equal, within agreed upon tolerances, to that of a reference sample agreed upon between the purchaser and the seller.

4. Sampling

4.1 Two samples shall be taken at random from different packages from each lot, batch, day's pack, or other unit of production in a shipment. When no markings distinguishing between units of production appear, samples shall be taken from different packages in the ratio of two samples for each 10 000 lb (5000 kg), except that for shipments of less than 10 000 lb, two samples shall be taken. At the option of the purchaser, the samples may be tested separately or after blending in equal quantities, the samples from the same production unit form a composite sample.

5. Test Methods

5.1 Tests shall be conducted in accordance with the following ASTM test methods, where applicable. Test procedures not covered by ASTM test methods shall be mutually agreed upon between the purchaser and the seller.

5.1.1 *Color, Composition, and Coarse Particles*—Test Methods D 717.

5.1.2 *Water-Soluble Matter and Loss on Ignition*—Test Methods D 1208.

5.1.3 *Oil Absorption*—Test Method D 281.

5.1.4 *Consistency*—Use the pigment to prepare a mixture according to the following directions: Weigh 78 g of petroleum spirits and 80 g of linseed oil (viscosity, 21 to 24 P; acid number, 4 to 8) into a pint can and thoroughly mix with a

spatula. Weigh in 160 g of magnesium silicate and stir with a spatula to wet all lumps. Stir with a motor-driven propeller-type stirrer for 5 min at approximately 800 r/min. Weigh in an additional 180 g of linseed oil and stir an additional 2 min with the electric stirrer. Determine the consistency in accordance with Test Method D 562.

5.1.5 *Fineness*—Test Method D 1210. The test mixture may be the same as that used for the consistency test.

5.1.6 *Moisture*—Test Methods D 280.

6. Keywords

6.1 hydrous magnesium silicate; magnesium silicate; pigment; talc

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.