



Standard Test Method for Evaluating Degree of Checking of Exterior Paints¹

This standard is issued under the fixed designation D 660; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 The illustrated reference standards included in this test method are representative of degrees and types of checking of exterior paint films. These standards are primarily intended for comparative evaluation.

2. Terminology

2.1 Definitions of Terms Specific to This Standard:

2.1.1 *checking, n*—that phenomenon manifested in paint films by slight breaks in the film that do not penetrate through the last applied coating. Where precision is necessary in evaluating a paint film, checking may be described as *visible* (as seen with the naked eye) or as *microscopic* (as observed under a magnification up to ten diameters).

3. Significance and Use

3.1 Since checking is not easily recognizable, this test method is intended to provide, through definition and illustrations, a means of evaluating the degree of this film failure.

4. Types of Checking

4.1 Many types of checking are recognized, of which some are:

4.1.1 *Irregular Pattern Type*—Checking in which the breaks develop in the surface of the film in no definite pattern.

4.1.2 *Line and Short Parallel Type*—Checking in which the breaks in the surface of the film are generally arranged in parallel lines.

4.1.3 *Switch Type*—Checking in which the breaks in the surface of the film form short and long irregular lines crossing each other in a wire brushed pattern.

4.1.4 *Crow Foot Type*—Checking in which the breaks in the surface of the film form in a definite three-pronged pattern with the breaks running from a center and forming an angle of about 120° between the prongs.

4.1.5 *Mosaic Type*—Checking in which the breaks in the

surface of the film form straight sided, geometric patterns which join on all sides.

4.1.6 *Shrinkage Type*—Checking in which the breaks in the surface of the film usually form individual short breaks with shorter irregular breaks progressing at right angles.

4.1.7 *Short, Random Type*—Checking in which breaks in the surface of the film form short, irregular patterns. These breaks are usually individual and do not join.

4.1.8 *Sigmoid Type*—Checking in which the breaks in the surface of the film form oval patterns. These oval shapes rarely complete their circle.

5. Use of Illustrated Reference Standards²

5.1 The use of the reference standards shown in Fig. 1 requires the following precautions:

5.1.1 Since the type and degree of failure may vary over any given area, a representative portion should be rated. It is recommended that ratings be made at several locations, noting types and degree of failure.

5.1.2 Care must be taken to recognize that several types of checking may be present on the same surface.

5.1.3 Paint films may collect excessive quantities of dirt, which may mask the type and degree of failure. If necessary, dirt should be removed by careful and gentle brushing with a moderately soft brush. Care must be taken not to damage the finish.

5.1.4 Fig. 2 illustrates microscopic checking under 10-diameter magnification.

5.1.5 For convenience in recording the data obtained, the records should be kept on forms agreed upon between the purchaser and the seller.

6. Precision and Bias

6.1 No precision or bias statement has been established for this test method.

7. Keywords


7.1 checking; evaluations; reference standards

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.25 on Pictorial Standards of Coating Defects.


Current edition approved May 15, 1993. Published July 1993. Originally published as D 660 – 44 T. Last previous edition D 660 – 87.

² TNO illustrated reference standards are provided as a courtesy of TNO (Toegepast Natuurwetenschappelijk Onderzoek), Schoemakerstraat 97, Delft, Netherlands.


5.1.1 IRREGULAR




ASTM 8
TNO 2



ASTM 6
TNO 4




ASTM 4
TNO 6




ASTM 2
TNO 8

FIG. 1 Illustrated Reference Standard




ASTM 8
TNO 2




ASTM 6
TNO 4


5.1.2 LONG
LINE




ASTM 4
TNO 6



ASTM 2
TNO 8




ASTM 8
TNO 2




ASTM 6
TNO 4

5.1.2 SHORT
PARALLEL




ASTM 4
TNO 6




ASTM 2
TNO 8

FIG. 1 (continued)


5.1.3 SWITCH




ASTM 8
TNO 2



ASTM 6
TNO 4




ASTM 4
TNO 6




ASTM 2
TNO 8

FIG. 1 (continued)


5.1.4 CROW FOOT




ASTM 8
TNO 2



ASTM 6
TNO 4




ASTM 4
TNO 6




ASTM 2
TNO 8

FIG. 1 (continued)


5.1.5 MOSAIC




ASTM 8
TNO 2



ASTM 6
TNO 4




ASTM 4
TNO 6




ASTM 2
TNO 8

FIG. 1 (continued)


5.1.6 SHRINKAGE




ASTM 8
TNO 2



ASTM 6.
TNO 4




ASTM 4
TNO 6




ASTM 2
TNO 8

FIG. 1 (continued)




ASTM 8
TNO 2




5.1.7 SHORT,
RANDOM

ASTM 6
TNO 4




ASTM 4
TNO 6




ASTM 2
TNO 8

FIG. 1 (continued)




ASTM 8
TNO 2




ASTM 6
TNO 4

5.1.8 SIGMOID



ASTM 4
TNO 6



ASTM 2
TNO 8

FIG. 1 (continued)



FIG. 2 No. 8 (Checking Magnified 10 Diameters)

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).