



## Standard Test Method for Burnish Resistance of Latex Paints<sup>1</sup>

This standard is issued under the fixed designation D 6736; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers a procedure for measuring the resistance of latex paints to burnishing under dry conditions.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*

D 523 Test Method for Specular Gloss<sup>2</sup>

D 2486 Test Methods for Scrub Resistance of Wall Paints<sup>3</sup>

D 3924 Specification for Standard Environment for Conditioning and Testing Paint, Varnish, Lacquer, and Related Materials<sup>2</sup>

### 3. Terminology

3.1 *Definition:*

3.1.1 *burnish resistance*—the ability of a coating to resist an increase in its gloss (sheen) value after polishing or rubbing.

### 4. Summary of Test Method

4.1 Test paints are drawn down lengthwise on plastic panels using a 0.18-mm (7.0-mil) applicator and allowed to air-dry for one week. Gloss readings are taken at three equally spaced points, lengthwise along the center of the panel. The panel is then rubbed for 20 cycles on a scrub machine, after which gloss readings are again taken along the same path abraded by the scrub machine. The initial values are averaged and the final values are averaged. The difference between the initial and final gloss readings, divided by the initial reading times 100 is a quantitative indication of the paint's resistance to burnishing. Higher percentage increases denote poorer resistance and vice-versa.

### 5. Significance and Use

5.1 Interior flat paints may become burnished in areas where

clothing or upholstered furniture rub against a wall. This rubbing may cause a smoother, glossier surface at the contacted area, depending on the level or type of pigments in the paint and binder hardness. This method permits a more quantitative estimate of burnish resistance than those using manual rubbing techniques.

### 6. Apparatus

6.1 Constant temperature/humidity room  $23 \pm 2^\circ\text{C}$  ( $73.5 \pm 3.5^\circ\text{F}$ );  $50 \pm 5\%$  relative humidity (standard conditions, Specification D 3924).

6.2 *Washability Machine (Scrub Machine)*, described in Test Methods D 2486.

6.2.1 *Accessory Apparatus:*

6.2.1.1 *Sandpaper Attachment*, total weight 454 g.

6.2.1.2 *Glass Plate*, measured to fit.

6.2.1.3 *Gasket Frame and Clamps*.

6.3 *Large Vacuum Plate*.

6.4 *Film Caster*, having a 0.18-mm (7.0-mil) clearance.

6.5 *Glossmeter(s)*, capable of measuring  $60^\circ$  and  $85^\circ$  gloss in accordance with Test Method D 523.

### 7. Materials

7.1 *Plastic Scrub Panels*, 43.5 mm  $\times$  16.5 mm (17 in.  $\times$  6.5 in.), white or black.

7.2 *Cheesecloth*, 4-ply, medium weave.<sup>4</sup>

### 8. Procedure

8.1 *Application and Evaluation of Test Paints:*

8.1.1 Attach a plastic panel to the vacuum plate and draw down the test paint uniformly lengthwise, using the 0.18-mm (7.0-mil) side of the applicator.

8.1.2 Condition the panels for one week in the constant temperature / humidity room or under other conditions agreed upon between the buyer and seller.

8.1.3 Take three equally spaced gloss readings (Test Method D 523) along the center length of the panel, making sure the areas of the readings are within the travel path of the scrub machine attachment. The resulting average of the three readings is used as the initial value prior to rubbing the panel. It is suggested that the gloss readings should be as follows:

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.42 on Architectural Coatings.

Current edition approved Dec. 10, 2001. Published February 2002.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 06.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 06.02.

<sup>4</sup> Bleached cheesecloth, grade 20B, 24/20 (medium) weave, available from de Royal Textiles, Camden, SC, was used in developing this method.

Semi-Gloss Paints	60°
Sheen Paints	60° and 85°
Flat Paints	85°

In general, if the 60° reading drops below 20 units the 85° reading should be recorded.

8.1.4 Secure one layer of 4-ply cheesecloth lengthwise in the sandpaper attachment of the scrub machine.

8.1.5 Secure the panel on the scrub machine over the glass plate using the gasket and clamps. Attach the sandpaper attachment to the scrub machine. Start the machine.

8.1.6 Abrade the panel for 20 reciprocating cycles. Stop the machine.

8.1.7 Remove the panel from the scrub machine and carefully clean off any loose pigment from the panel. Re-read the panel, again taking three equally spaced gloss readings along path of the burnished area. Average the values and use this average as the final after burnishing value.

## 9. Report

9.1 Report the following information:

9.1.1 The application clearance, if different than those specified in this test method.

9.1.2 The drying time and conditions used, if different than those specified in this test method.

9.1.3 The number of cycles used in abrading the panels, if different than the number specified in this test method.

9.1.4 The gloss angles used and the initial and final gloss units.

9.1.5 The total weight the sandpaper attachment used in the test.

9.1.6 The percent increase in gloss calculated by subtracting the initial average reading from the final average reading, dividing by the initial reading, and multiplying by 100.

## 10. Precision and Bias

10.1 *Precision*—To be determined.

10.2 *Bias*—Statement to be added.

## 11. Keywords

11.1 abrasion resistance; burnish resistance; polishing

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*