



## Standard Test Method for Evaluating Degree of Settling of Paint<sup>1</sup>

This standard is issued under the fixed designation D 869; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This test method covers the determination of the degree of pigment suspension and ease of remixing a shelf-aged sample of paint to a homogeneous condition suitable for the intended use.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 1309 Test Method for Settling Properties of Traffic Paints During Accelerated Storage<sup>2</sup>

### 3. Significance and Use

3.1 Paints, if not formulated or processed properly may settle excessively. Paint that settles excessively is difficult to reincorporate into the paint system causing time delays or valuable pigment being left in the drum. This test method is an attempt to evaluate the degree of settling caused by the accelerated Test Method D 1309. This very subjective method of evaluation in conjunction with the variables of Test Method D 1309 raises questions as to the usefulness of the results for specification compliance.

### 4. Apparatus

4.1 *Container*, standard 1-pt (500-mL) friction-top can paint container,  $3\frac{3}{8} \pm \frac{1}{16}$  in. ( $85.5 \pm 1.5$  mm) in diameter, and  $3\frac{7}{8} \pm \frac{1}{16}$  in. ( $98.5 \pm 1.5$  mm) in height.

4.2 *Spatula*, weighing  $45 \pm 1$  g with square-end blade  $4\frac{3}{4}$  in. (125 mm) in length and approximately  $1\frac{3}{16}$  in. (20 mm) in

width, shall be used to examine the paint for pigment settling and reincorporation characteristics.

### 5. Procedure

5.1 Place the specimen to be tested for pigment suspension in a 1-pt (500-mL) container, filling the can to within  $\frac{1}{2}$  in. (13 mm) of the top. Close the can tightly and hold undisturbed for shelf aging for 6 months or for such other periods of time agreed upon between the purchaser and the seller.

5.2 Open the can holding the shelf-aged sample without shaking or agitation, and examine the sample without removal of supernatant vehicle. Use the spatula to determine the extent and character of portions of the paint that may have separated during storage. Prepare a suitable spatula for this purpose by cutting the tip from an ordinary 5-in. (127-mm) flexible steel laboratory spatula to the specified length. Hold the spatula perpendicular to and in the center area of the paint at a height whereby the bottom edge of the spatula is level with the top of the can. Drop the spatula from that position. Rate the condition of the sample in accordance with 5.4.

5.3 After examination of the entire specimen as described in 5.2, if a portion of the pigment has separated out to form a firm cake at the bottom of the container pour the supernatant portion of the liquid off into a clean container and hold for subsequent use. Reincorporate the separate cake by hand stirring with the spatula, adding back the liquid in small amounts until the pigment has been reincorporated to form a homogeneous paint suitable for the intended use or until it is determined that the pigment cake cannot be reincorporated by hand stirring. Rate the condition of the specimen in accordance with 5.4.

5.4 Rate the sample for degree of settling on a scale from 10 to 0 in accordance with the following. Give intermediate conditions the appropriate odd number.

Rating	Description of Paint Condition
10	Perfect suspension. No change from the original condition of the paint.
8	A definite feel of settling and a slight deposit brought up on spatula. No significant resistance to sidewise movement of spatula.
6	Definite cake of settled pigment. Spatula drops through cake to bottom of container under its own weight. Definite resistance to sidewise motion of spatula. Coherent portions of cake may be removed on spatula.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D011 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.44 on Traffic Coatings.

Current edition approved Sept. 27, 1985. Published November 1985. Originally published as D 869 – 46 T. Last previous edition D 869 – 78.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 06.02.

Rating	Description of Paint Condition
4	Spatula does not fall to bottom of container under its own weight. Difficult to move spatula through cake sidewise and slight edgewise resistance. Paint can be remixed readily to a homogeneous state.
2	When spatula has been forced through the settled layer it is very difficult to move spatula sidewise. Definite edgewise resistance to movement of spatula. Paint can be remixed to a homogeneous state.
0	Very firm cake that cannot be reincorporated with the liquid to form a smooth paint by stirring manually.

method, if it is used in a specification, the maximum deviation from the settling limits specified should be agreed upon between the purchaser and the seller.

6.2 *Bias*—Bias cannot be determined.

## 7. Keywords

7.1 paint testing; paint settling; settling test pigment suspension

## 6. Precision and Bias

6.1 *Precision*—Due to the poor precision of this test

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*