



Standard Specification for Penetration-Graded Asphalt Cement for Use in Pavement Construction¹

This standard is issued under the fixed designation D 946; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers asphalt cement for use in the construction of pavements.

1.2 This specification covers the following penetration grades:

40–50,	120–150, and
60–70,	200–300.
85–100,	

2. Referenced Documents

2.1 ASTM Standards:

- D 5 Test Method for Penetration of Bituminous Materials²
- D 92 Test Method for Flash and Fire Points by Cleveland Open Cup³
- D 113 Test Method for Ductility of Bituminous Materials²
- D 140 Practice for Sampling Bituminous Materials²
- D 1754 Test Method for Effect of Heat and Air on Asphaltic

¹ This specification is under the jurisdiction of ASTM Committee D-4 on Road and Paving Materials and is the direct responsibility of Subcommittee D 04.40 on Asphalt Specifications.

Current edition approved Feb. 5, 1982. Published April 1982. Originally published as D 946 – 47 T. Last previous edition D 946 – 74 (1980).

² *Annual Book of ASTM Standards*, Vol 04.03.

³ *Annual Book of ASTM Standards*, Vol 05.01.

Materials (Thin-Film Oven Test)²

D 2042 Test Method for Solubility of Asphalt Materials in Trichloroethylene²

3. Manufacture

3.1 Asphalt cement shall be prepared by the refining of crude petroleum by suitable methods.

4. Properties

4.1 The asphalt cement shall be homogeneous and shall not foam when heated to 347°F (174°C).

4.2 The various grades of asphalt cement shall conform to the requirements prescribed in Table 1.

5. Methods of Sampling and Testing

5.1 The material shall be sampled and the properties enumerated in this specification shall be determined in accordance with the following ASTM methods:

5.1.1 *Sampling*—Practice D 140.

5.1.2 *Penetration*—Test Method D 5.

5.1.3 *Flash Point*—Test Method D 92.

5.1.4 *Ductility*—Test Method D 113.

5.1.5 *Thin Film Oven Test*—Test Method D 1754.

5.1.6 *Solubility in Trichloroethylene*—Test Method D 2042.

TABLE 1 Requirements for Asphalt Cement for Use in Pavement Construction

	Penetration Grade									
	40–50		60–70		85–100		120–150		200–300	
	Min	Max	Min	Max	Min	Max	Min	Max	Min	Max
Penetration at 77°F (25°C) 100 g, 5 s	40	50	60	70	85	100	120	150	200	300
Flash point, °F (Cleveland open cup)	450	...	450	...	450	...	425	...	350	...
Ductility at 77°F (25°C) 5 cm/min, cm	100	...	100	...	100	...	100	...	100 ^A	...
Solubility in trichloroethylene, %	99.0	...	99.0	...	99.0	...	99.0	...	99.0	...
Retained penetration after thin-film oven test, %	55 +	...	52 +	...	47 +	...	42 +	...	37 +	...
Ductility at 77°F (25°C) 5 cm/min, cm after thin-film oven test test	50	...	75	...	100	...	100 ^A	...

^AIf ductility at 77°F (25°C) is less than 100 cm, material will be accepted if ductility at 60°F (15.5°C) is 100 cm minimum at the pull rate of 5 cm/min.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (<http://www.astm.org>).