



Standard Specification for Raw Castor Oil¹

This standard is issued under the fixed designation D 960; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers castor oil suitable for use in resins and protective coatings, including lacquers. This is generally known in the trade as No. 1 castor oil.

2. Referenced Documents

2.1 ASTM Standards:

D 555 Guide for Testing Drying Oils²

D 1466 Test Method for Sampling Liquid Oils and Fatty Acids Commonly Used in Paints, Varnishes, and Related Materials²

D 1544 Test Method for Color of Transparent Liquids (Gardner Color Scale)³

D 1545 Test Method for Viscosity of Transparent Liquids by Bubble Time Method²

D 1639 Test Method for Acid Value of Organic Coating Materials²

D 1957 Test Method for Hydroxyl Value of Fatty Oils and Acids²

D 1959 Test Method for Iodine Value of Drying Oils and Fatty Acids²

D 1960 Test Method for Loss on Heating of Drying Oils²

D 1962 Test Method for Saponification Value of Drying Oils, Fatty Acids, and Polymerized Fatty Acids²

D 1963 Test Method for Specific Gravity of Drying Oils, Varnishes, Resins, and Related Materials at 25/25°C²

D 1965 Test Method for Unsaponifiable Matter in Drying Oils, Fatty Acids, and Polymerized Fatty Acids²

D 2090 Test Method for Clarity and Cleanness of Paint and Ink Liquids²

¹ This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.32 on Drying Oils.

Current edition approved Dec. 10, 2002. Published February 2003. Originally approved in 1963. Last previous edition approved in 2002 as D 960 – 02.

² Annual Book of ASTM Standards, Vol 06.03.

³ Annual Book of ASTM Standards, Vol 06.01.

TABLE 1 Properties of Castor Oil

Property	Requirement	ASTM Test Method
Acid value, max	2.0	D 1639
Clarity	clear	D 2090
Color (Gardner), max	3	D 1544
Hydroxyl value	160 to 168	D 1957
Loss on heating, max, %	0.25	D 1960
Refractive index, 25°C	1.4764 to 1.4778	...
Saponification value	176 to 184	D 1962
Solubility in alcohol ^A	complete	...
Specific gravity, 25/25°C	0.957 to 0.961	D 1963
Unsaponifiable, max, %	0.7	D 1965
Viscosity, St	6.3 to 8.9	D 1545
Iodine value	83 to 88	D 1959
Ricinoleic Acid Content	85 % min	ISO 5008/9

^ACastor oil shall be completely soluble without turbidity at 20°C in two volumes of specifically denatured alcohol (95 %) conforming to Formula 3A of U. S. Bureau of Alcohol, Tobacco, and Firearms.

3. Properties

3.1 Castor oil shall conform to the requirements given in Table 1.

4. Test Methods

4.1 The properties enumerated in this specification shall be determined in accordance with the ASTM test methods listed in Table 1.

5. Sampling

5.1 Sampling shall be conducted in accordance with Test Method D 1466.

6. Significance and Use

6.1 The significance of the test methods enumerated under Section 2 of this specification is discussed in Guide D 555.

7. Keywords

7.1 castor oil; non-drying oils

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).