



Standard Specification for Industrial Grade Ethylene Glycol¹

This standard is issued under the fixed designation E 1119; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers industrial grade ethylene glycol.

1.2 The following precautionary caveat pertains only to the test method portion, Section 5, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.3 Review the current Materials Safety Data Sheets (MSDS) for detailed information concerning toxicity, first aid procedures, handling and safety precautions.

2. Referenced Documents

2.1 ASTM Standards:

- E 202 Test Methods for Analysis of Ethylene Glycols and Propylene Glycols²
- E 300 Practice for Sampling Industrial Chemicals²
- E 347 Test Method for Ash in Polybasic Acids²

3. Requirements

3.1 Industrial grade ethylene glycol shall conform to the

following chemical and physical requirements:

		ASTM Test Method
Ethylene Glycol, % by weight	99.0 min	E 202
Diethylene Glycol, % by weight	0.5 max	E 202
Other Glycols, % by weight	0.1 max	E 202
Total Glycols, % by weight	99.5 min	E 202
Water, % by weight	0.3 max	E 202
Acidity as Acetic Acid, % by weight	0.005 max	E 202
Ash, % by weight	0.0045 max	E 347
Color, Platinum-Cobalt	10.0 max	E 202
Apparent Specific Gravity		
20/20°C	1.1151–1.1156	E 202
25/25°C	1.1129–1.1134	
Distillation Range, 760 mm Hg		
Initial boiling point, °C	193 min	E 202
Dry point, °C	204 max	

4. Sampling

4.1 Sample ethylene glycol in accordance with the appropriate sections of Practice E 300 for liquid samples.

5. Test Methods

5.1 Test each composite sample for chemical and physical requirements using the test methods specified in 3.1.


6. Keywords

6.1 ethylene glycol; industrial grade

¹ This specification is under the jurisdiction of ASTM Committee E15 on Industrial and Specialty Chemicals and is the direct responsibility of Subcommittee E15.02 on Product Standards.

Current edition approved July 10, 1997. Published June 1998. Originally published as E 1119 – 86. Last previous edition E 1119 – 92.

² *Annual Book of ASTM Standards*, Vol 15.05.

 **E 1119**

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).